

Product Reference: Miothene 30

Product Description: Closed Cell Polyethylene Foam

Specification

Properties	Values	Standard
Nominal Density	30 Kg/m ³	ASTM D3575-08 Suffix W ISO 845:2006
Cell Size	≥26 Cells	BS 4443/1 Met.4
Compressive strength at 25% (4 th compression) (100mm/min compression speed)	30KPa	ISO 3386 1986 part 1 DIN 53577
Compressive strength at 50% (4 th compression) (100mm/min compression speed)	90KPa	ISO 3386 1986 part 1 DIN 53577
Compressive strength at 70% (4 th compression) (100mm/min compression speed)	205KPa	ISO 3386 1986 part 1 DIN 53577
Compressive Strength Vertical @ 25% (100mm/min compression speed)	45KPa	ASTM D3578-08 Suffix D OSO7214:2007
Compressive Strength Vertical @ 50% (100mm/min compression speed)	95KPa	ASTM D3578-08 Suffix D OSO7214:2007
Compression set	<10%	ASTM D3575-08 Suffix B 50% Compression
Compressive Creep (1.25psi – 8.75 kg/dm ²)	<10%	ASTM D3575-08 Suffix BB 168 hrs
Compressive Creep (1.25psi – 8.75 kg/dm ²)	<15%	ASTM D3575-08 Suffix BB 1000 hrs
Water Absorption	<3 Volume%	ASTM D3575-08 Suffix L ISO 2896:1986
Thermal Conductivity	0.05W/mK	ASTM C-177 ISO 8301
Thermal Stability (24hrs at 70°C)	<2%	ASTM D3575-08 Suffix S ISO 2796
Tear Strength (MD/CD)	17N/cm 18N/cm	ASTM D3575-08 Suffix G
Tensile Strength @ peak (MD/CD)	250KPa 200KPa	ASTM D3575-08-Suffix T Iso 1798:2008
Tensile Elongation (MD/CD)	70% 65%	ASTM D3575-08 ISO 1798:2008
Flame Retardant Version	1 Class	UL 94HF
Fire-Test Response Characteristics	Pass	FMVSS 302

(1) These numerical laboratory fire-test-response characteristics are not intended to reflect hazards presented by material under actual fire conditions.